

Battery Pack Test Report

UN38.3

Customer: Lenovo

Pack Model: L10C3Z11

Nominal voltage: 11.1V dc

Nominal capacity: 2200mAh/24Wh

Configuration: 3S1P

Customer P/N: 121001129(黑)/121001128(白)

1209-00179 (BLD) (黑)

Celxpert P/N: 921300044(黑)/921300045(白)

Cell Type: LG S3 2.2Ah

Jan. 29, 2018

Approved by _____

Reviewed by _____

Prepared by _____




Figure photo of the pack.



1. UN38.3 Test Report

Test Period	2010/11/20~2010/12/10		Test Spec.	ST/SG/AC.10/11/Rev.4	
Parts Name	Battery Pack	Application	NB	Quantity	16PCS

1.1 Test Summary

Item	Test Item	Test Result	Details
T1	Altitude simulation test (UN38.3-1)	Pass	Page 9
T2	Thermal test (UN38.3-2)	Pass	Page 10
T3	Vibration test (UN38.3-3)	Pass	Page 11
T4	Shock test (UN38.3-4)	Pass	Page 12
T5	Short Circuit test (UN38.3-5)	Pass	Page 13
T6	Impact Test (UN38.3-6)	Pass	Page 13
T7	Overcharge test (UN38.3-7)	Pass	Page 14

The battery pack passes UN38.3 test.

1.2 Test sample list

No.	Pack S/N	Test item	No.	Cell Num.	Test item
1	Sample No:1/16	38.3.1~5	1	H3634100298	38.3.6
2	Sample No:2/16	38.3.1~5	2	H3634100257	38.3.6
3	Sample No:3/16	38.3.1~5	3	H3634103196	38.3.6
4	Sample No:4/16	38.3.1~5	4	H3634100503	38.3.6
5	Sample No:5/16	38.3.1~5	5	H3634100227	38.3.6
6	Sample No:6/16	38.3.1~5	6		
7	Sample No:7/16	38.3.1~5	7		
8	Sample No:8/16	38.3.1~5	8		
9	Sample No:9/16	38.3.7	9		
10	Sample No:10/16	38.3.7	10		
11	Sample No:11/16	38.3.7			
12	Sample No:12/16	38.3.7			
13	Sample No:13/16	38.3.7			
14	Sample No:14/16	38.3.7			
15	Sample No:15/16	38.3.7			
16	Sample No:16/16	38.3.7			

1.3 Test result

Item	Test Item	Test specification	Judge criteria	Sample(s)								
T1	Altitude Simulation (UN38.3-1)	1-1.4 batteries are standard charged. 4 batteries are 1C cycled 50 times, ending in fully charged state. All batteries weight is measured. The charged batteries voltage are measured and recorded. 1-2. Batteries shall be stored at a pressure of 11.6Kpa or less for at least six hours at ambient temperature 20+/-5 °C. 1-3. Vacuum is released. All cells weight is measured. The charged cell voltage are measured and recorded.	No mass loss (<0.1%), no leakage, no venting, no disassembly, no rupture and no fire. Battery voltage drop < 10%. Battery resistance change < ±10%.	4 packs are standard charged (Pack#1~4) 4 packs 50 cycled ending in fully charged states (Pack#5~8)								
Test Period		Start: 2010/11/20 End: 2010/11/20										
Test Equipment		數位電表 Q153, 真空烘箱 Q146, 天平 Q090										
Major Problem		-										
Warning Point		-										
Recommendation		The battery packs pass the test.										
Raw Data		Altitude Simulation Test on Charged Packs										
		No.	Before			After			Difference			Result
			OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)	
		1	12.5036	139.70	175.10	12.4826	140.26	175.09	0.17%	0.40%	0.01%	Pass
		2	12.4950	140.70	175.18	12.4725	140.32	175.18	0.18%	0.27%	0.00%	Pass
		3	12.4795	139.50	175.08	12.4636	139.68	175.06	0.13%	0.13%	0.01%	Pass
		4	12.5038	139.68	175.26	12.4791	139.64	175.26	0.20%	0.03%	0.00%	Pass
		5	12.4973	139.81	175.30	12.4806	139.26	175.30	0.13%	0.39%	0.00%	Pass
		6	12.4866	140.26	175.20	12.4716	140.51	175.18	0.12%	0.18%	0.01%	Pass
		7	12.4987	140.67	175.13	12.4811	140.83	175.11	0.14%	0.11%	0.01%	Pass
8	12.5028	139.92	175.15	12.4806	140.09	175.15	0.18%	0.12%	0.00%	Pass		

Item	Test Item	Test specification	Judge criteria	Sample(s)
T2	Thermal test (UN38.3-2)	2-1. Packs are stored for 6 hours at 75±2°C, followed by storage for 6 hours at -40±2°C. The maximum time interval between test temperature extremes is 30 minutes. 2-2.Repeat 2-1 for 10 times. Then store the packs at ambient for 24 hours. All packs weight are measured. The charged battery voltage are measured and recorded.	No mass loss (<0.1%), no leakage, no venting, no disassembly, no rupture and no fire. Battery voltage drop < 10%. Battery resistance change < ±10%.	4 packs are standard charged (Pack#1~4) 4 packs 50 cycled ending in fully charged states (Pack#5~8)

Test Period **Start: 2010/11/21 End: 2010/11/28**

Test Equipment 數位電表 Q153, 冷熱衝擊機 Q155, 天平 Q090

Major Problem -

Warning Point -

Recommendation **The packs pass the test.**

Thermal Test on Charged Packs										
No.	Before			After			Difference			Result
	OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)	
1	12.4826	140.26	175.09	12.4036	140.45	175.08	0.63%	0.14%	0.01%	Pass
2	12.4725	140.32	175.18	12.4026	140.53	175.16	0.56%	0.15%	0.01%	Pass
3	12.4636	139.68	175.06	12.3986	140.05	175.04	0.52%	0.26%	0.01%	Pass
4	12.4791	139.64	175.26	12.4035	140.11	175.25	0.61%	0.34%	0.01%	Pass
5	12.4806	139.26	175.30	12.4019	139.86	175.28	0.63%	0.43%	0.01%	Pass
6	12.4716	140.51	175.18	12.4033	140.78	175.15	0.55%	0.19%	0.02%	Pass
7	12.4811	140.83	175.11	12.4028	141.03	175.09	0.63%	0.14%	0.01%	Pass
8	12.4806	140.09	175.15	12.4042	140.62	175.13	0.61%	0.38%	0.01%	Pass

Raw Data

Item	Test Item	Test specification	Judge criteria	Sample(s)																																																																																																																													
T3	Vibration test (UN38.3-3)	3-1. Packs are firmly secured to the platform of the vibration machine without distorting the packs in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of 3 mutually perpendicular to the terminal face. 3-2. The logarithmic frequency sweep is as follows: 7-18 Hz → 1gn 18-50 Hz → 0.8mm amplitude 50-200 Hz → 8gn 3-3. All packs weight are measured. The charged packs voltage are measured and recorded.	No mass loss (<0.1%), no leakage, no venting, no disassembly, no rupture and no fire. Battery voltage drop < 10%. Battery resistance change < ±10%	4 packs are standard charged (Pack#1~4) 4 packs 50 cycled ending in fully charged states (Pack#5~8)																																																																																																																													
Test Period		Start: 2010/11/29 End: 2010 /11/30																																																																																																																															
Test Equipment		數位電表 Q153, 振動測試機 Q300, 天平 Q090																																																																																																																															
Major Problem		-																																																																																																																															
Warning Point		-																																																																																																																															
Recommendation		The packs pass the test.																																																																																																																															
Raw Data		<table border="1"> <thead> <tr> <th colspan="11">Vibration Test on Charged Packs</th> </tr> <tr> <th rowspan="2">No.</th> <th colspan="3">Before</th> <th colspan="3">After</th> <th colspan="3">Difference</th> <th rowspan="2">Result</th> </tr> <tr> <th>OCV (V)</th> <th>Resistance (mΩ)</th> <th>Weight (g)</th> <th>OCV (V)</th> <th>Resistance (mΩ)</th> <th>Weight (g)</th> <th>Volt (%)</th> <th>Resistance (%)</th> <th>Weight (%)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>12.4036</td> <td>140.45</td> <td>175.08</td> <td>12.3833</td> <td>140.63</td> <td>175.07</td> <td>0.16%</td> <td>0.13%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>2</td> <td>12.4026</td> <td>140.53</td> <td>175.16</td> <td>12.3842</td> <td>140.77</td> <td>175.15</td> <td>0.15%</td> <td>0.17%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>3</td> <td>12.3986</td> <td>140.05</td> <td>175.04</td> <td>12.3802</td> <td>140.32</td> <td>175.01</td> <td>0.15%</td> <td>0.19%</td> <td>0.02%</td> <td>Pass</td> </tr> <tr> <td>4</td> <td>12.4035</td> <td>140.11</td> <td>175.25</td> <td>12.3846</td> <td>140.29</td> <td>175.22</td> <td>0.15%</td> <td>0.13%</td> <td>0.02%</td> <td>Pass</td> </tr> <tr> <td>5</td> <td>12.4019</td> <td>139.86</td> <td>175.28</td> <td>12.3852</td> <td>140.02</td> <td>175.24</td> <td>0.13%</td> <td>0.11%</td> <td>0.02%</td> <td>Pass</td> </tr> <tr> <td>6</td> <td>12.4033</td> <td>140.78</td> <td>175.15</td> <td>12.3826</td> <td>140.99</td> <td>175.13</td> <td>0.17%</td> <td>0.15%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>7</td> <td>12.4028</td> <td>141.03</td> <td>175.09</td> <td>12.3844</td> <td>141.42</td> <td>175.05</td> <td>0.15%</td> <td>0.28%</td> <td>0.02%</td> <td>Pass</td> </tr> <tr> <td>8</td> <td>12.4042</td> <td>140.62</td> <td>175.13</td> <td>12.3835</td> <td>140.89</td> <td>175.10</td> <td>0.17%</td> <td>0.19%</td> <td>0.02%</td> <td>Pass</td> </tr> </tbody> </table>									Vibration Test on Charged Packs											No.	Before			After			Difference			Result	OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)	1	12.4036	140.45	175.08	12.3833	140.63	175.07	0.16%	0.13%	0.01%	Pass	2	12.4026	140.53	175.16	12.3842	140.77	175.15	0.15%	0.17%	0.01%	Pass	3	12.3986	140.05	175.04	12.3802	140.32	175.01	0.15%	0.19%	0.02%	Pass	4	12.4035	140.11	175.25	12.3846	140.29	175.22	0.15%	0.13%	0.02%	Pass	5	12.4019	139.86	175.28	12.3852	140.02	175.24	0.13%	0.11%	0.02%	Pass	6	12.4033	140.78	175.15	12.3826	140.99	175.13	0.17%	0.15%	0.01%	Pass	7	12.4028	141.03	175.09	12.3844	141.42	175.05	0.15%	0.28%	0.02%	Pass	8	12.4042	140.62	175.13	12.3835	140.89	175.10	0.17%	0.19%	0.02%	Pass
Vibration Test on Charged Packs																																																																																																																																	
No.	Before			After			Difference			Result																																																																																																																							
	OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)																																																																																																																								
1	12.4036	140.45	175.08	12.3833	140.63	175.07	0.16%	0.13%	0.01%	Pass																																																																																																																							
2	12.4026	140.53	175.16	12.3842	140.77	175.15	0.15%	0.17%	0.01%	Pass																																																																																																																							
3	12.3986	140.05	175.04	12.3802	140.32	175.01	0.15%	0.19%	0.02%	Pass																																																																																																																							
4	12.4035	140.11	175.25	12.3846	140.29	175.22	0.15%	0.13%	0.02%	Pass																																																																																																																							
5	12.4019	139.86	175.28	12.3852	140.02	175.24	0.13%	0.11%	0.02%	Pass																																																																																																																							
6	12.4033	140.78	175.15	12.3826	140.99	175.13	0.17%	0.15%	0.01%	Pass																																																																																																																							
7	12.4028	141.03	175.09	12.3844	141.42	175.05	0.15%	0.28%	0.02%	Pass																																																																																																																							
8	12.4042	140.62	175.13	12.3835	140.89	175.10	0.17%	0.19%	0.02%	Pass																																																																																																																							

Item	Test Item	Test specification	Judge criteria	Sample(s)																																																																																																																														
T4	Shock test (UN38.3-4)	<p>4-1. Packs shall be secured to the testing machine by means of a rigid mount, which will support all mounting surfaces.</p> <p>4-2. Packs shall be subjected to a half-sine shock of peak acceleration 150gn and pulse duration of 6 milliseconds. Each pack shall be subjected to 3 shocks in the positive direction followed by three shocks in the negative direction of three mutually perpendicularly mounting positions of the pack for a total of 18 shocks.</p> <p>4-3. All batteries weight are measured. The charged cell voltage are measured and recorded.</p>	<p>No mass loss (<0.1%), no leakage, no venting, no disassembly, no rupture and no fire.</p> <p>Battery voltage drop < 10%.</p> <p>Battery resistance change < ±10%.</p>	<p>4 packs are standard charged (Pack#1~4)</p> <p>4 packs 50 cycled ending in fully charged states (Pack#5~8)</p>																																																																																																																														
Test Period		Start: 2010/12/1 End: 2010/12/1																																																																																																																																
Test Equipment		數位電表 Q153, 衝擊測試機 Q154, 天平 Q090																																																																																																																																
Major Problem		-																																																																																																																																
Warning Point		-																																																																																																																																
Recommendation		The packs pass the test.																																																																																																																																
Raw Data		<table border="1"> <thead> <tr> <th colspan="11">Shock Test on Charged Packs</th> </tr> <tr> <th rowspan="2">No.</th> <th colspan="3">Before</th> <th colspan="3">After</th> <th colspan="3">Difference</th> <th rowspan="2">Result</th> </tr> <tr> <th>OCV (V)</th> <th>Resistance (mΩ)</th> <th>Weight (g)</th> <th>OCV (V)</th> <th>Resistance (mΩ)</th> <th>Weight (g)</th> <th>Volt (%)</th> <th>Resistance (%)</th> <th>Weight (%)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>12.3833</td> <td>140.63</td> <td>175.07</td> <td>12.3659</td> <td>140.88</td> <td>175.06</td> <td>0.14%</td> <td>0.18%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>2</td> <td>12.3842</td> <td>140.77</td> <td>175.15</td> <td>12.3684</td> <td>140.92</td> <td>175.14</td> <td>0.13%</td> <td>0.11%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>3</td> <td>12.3802</td> <td>140.32</td> <td>175.01</td> <td>12.3639</td> <td>140.53</td> <td>175.01</td> <td>0.13%</td> <td>0.15%</td> <td>0.00%</td> <td>Pass</td> </tr> <tr> <td>4</td> <td>12.3846</td> <td>140.29</td> <td>175.22</td> <td>12.3661</td> <td>140.56</td> <td>175.20</td> <td>0.15%</td> <td>0.19%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>5</td> <td>12.3852</td> <td>140.02</td> <td>175.24</td> <td>12.3649</td> <td>140.32</td> <td>175.22</td> <td>0.16%</td> <td>0.21%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>6</td> <td>12.3826</td> <td>140.99</td> <td>175.13</td> <td>12.3675</td> <td>141.18</td> <td>175.11</td> <td>0.12%</td> <td>0.13%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>7</td> <td>12.3844</td> <td>141.42</td> <td>175.05</td> <td>12.3660</td> <td>141.66</td> <td>175.04</td> <td>0.15%</td> <td>0.17%</td> <td>0.01%</td> <td>Pass</td> </tr> <tr> <td>8</td> <td>12.3835</td> <td>140.89</td> <td>175.10</td> <td>12.3681</td> <td>141.02</td> <td>175.07</td> <td>0.12%</td> <td>0.09%</td> <td>0.02%</td> <td>Pass</td> </tr> </tbody> </table>										Shock Test on Charged Packs											No.	Before			After			Difference			Result	OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)	1	12.3833	140.63	175.07	12.3659	140.88	175.06	0.14%	0.18%	0.01%	Pass	2	12.3842	140.77	175.15	12.3684	140.92	175.14	0.13%	0.11%	0.01%	Pass	3	12.3802	140.32	175.01	12.3639	140.53	175.01	0.13%	0.15%	0.00%	Pass	4	12.3846	140.29	175.22	12.3661	140.56	175.20	0.15%	0.19%	0.01%	Pass	5	12.3852	140.02	175.24	12.3649	140.32	175.22	0.16%	0.21%	0.01%	Pass	6	12.3826	140.99	175.13	12.3675	141.18	175.11	0.12%	0.13%	0.01%	Pass	7	12.3844	141.42	175.05	12.3660	141.66	175.04	0.15%	0.17%	0.01%	Pass	8	12.3835	140.89	175.10	12.3681	141.02	175.07	0.12%	0.09%	0.02%	Pass
Shock Test on Charged Packs																																																																																																																																		
No.	Before			After			Difference			Result																																																																																																																								
	OCV (V)	Resistance (mΩ)	Weight (g)	OCV (V)	Resistance (mΩ)	Weight (g)	Volt (%)	Resistance (%)	Weight (%)																																																																																																																									
1	12.3833	140.63	175.07	12.3659	140.88	175.06	0.14%	0.18%	0.01%	Pass																																																																																																																								
2	12.3842	140.77	175.15	12.3684	140.92	175.14	0.13%	0.11%	0.01%	Pass																																																																																																																								
3	12.3802	140.32	175.01	12.3639	140.53	175.01	0.13%	0.15%	0.00%	Pass																																																																																																																								
4	12.3846	140.29	175.22	12.3661	140.56	175.20	0.15%	0.19%	0.01%	Pass																																																																																																																								
5	12.3852	140.02	175.24	12.3649	140.32	175.22	0.16%	0.21%	0.01%	Pass																																																																																																																								
6	12.3826	140.99	175.13	12.3675	141.18	175.11	0.12%	0.13%	0.01%	Pass																																																																																																																								
7	12.3844	141.42	175.05	12.3660	141.66	175.04	0.15%	0.17%	0.01%	Pass																																																																																																																								
8	12.3835	140.89	175.10	12.3681	141.02	175.07	0.12%	0.09%	0.02%	Pass																																																																																																																								

Item	Test Item	Test specification	Judge criteria	Sample(s)	
T5	Short Circuit Test (UN38.3-5)	5-1.Packs are placed in to a 55±2°C oven, and exterior packs temperature are monitored 5-2.When packs exterior reach 55±2°C, they are shorted by connecting terminals with a copper wire of resistance less than 100m Ohm. 5-4. The short was continued for more than 1hour or the cell temperature return to 55°C. The packs are observed for a further 6 hours.	No rupture, no disassembly, no explosion, no fire, no smoke. Packs exterior peak temperature <170°C.	4 packs are standard charged (Pack#1~4) 4 packs 50 cycled ending in fully charged states (Pack#5~8)	
Test Period		Start: 2010/12/2 End: 2010/12/4			
Test Equipment		數位電表 Q153, 資料收集器 Q078, 烘箱 Q171			
Recommendation		The packs pass the test.			
Raw Data		Short Circuit Test on Charged Packs			
		No.	Max. Temp.(°C)	Visual	Result
		1	56.15	OK	Pass
		2	56.20	OK	Pass
		3	56.14	OK	Pass
		4	56.13	OK	Pass
		5	55.89	OK	Pass
		6	56.07	OK	Pass
		7	55.93	OK	Pass
		8	56.14	OK	Pass
T6	Impact test (UN38.3-6)	6-1. The test sample is to be placed on a flat surface. A 15.8mm diameter bar is to be placed across the center of the sample. A 9.1 Kg mass is to be dropped from a height of 61±2.5cm onto the sample. 6-2. A cylindrical or prismatic cell is to be impacted with its longitudinal axis parallel to the flat surface.	External temperature of cell does not exceed 170°C and there is no disassembly and no fire within 6 hours of the test.	5 cells are 50% charged (Cell #1~5) For prismatic cell, The amount double	
Test Period		Start: 2010/11/25 End: 2010/11/26			
Test Equipment		數位電表 Q153, 資料收集器 Q160, 撞擊試驗機 Q231			
Recommendation		The Cells pass the test.			
Raw Data		Impact Test on 50% Charged Cells			
		No.	Max. Temp.(°C)	Visual	Result
		1	30.56	OK	Pass
		2	29.45	OK	Pass
		3	27.68	OK	Pass
		4	28.65	OK	Pass
		5	29.59	OK	Pass
Item	Test Item	Test specification	Judge criteria	Sample(s)	

T7	Overcharge test (UN38.3-7)	<p>7-1. The charge current shall be twice the Spec's recommended maximum continuous charge current.</p> <p>7-2. The minimum voltage of the test shall be as follows: (a) When the Spec's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. (b) When the Spec's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.</p> <p>7-3. Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours.</p>	No disassembly, no fire within seven days of the test.	4 packs are fully charged (Pack#9~12) 4 packs are 50 times cycled ending in fully charged state (Pack #13~16)		
Test Period	Start: 2010/12/2 End: 2010/12/10					
Test Equipment	數位電表 Q153, 資料收集器 Q151, 電源供應器 Q147					
Major Problem	-					
Warning Point	-					
Recommendation	The packs pass the test.					
Raw Data	Overcharge Test on Charged Packs					
	No.	Charge Voltage(V)	Charge Current(A)	Max. Temp.(°C)	Visual	Result
	9	22.0 V	2.2 A	25.07	OK	Pass
	10			25.63	OK	Pass
	11			25.48	OK	Pass
	12			25.34	OK	Pass
	13			25.13	OK	Pass
	14			24.86	OK	Pass
	15			25.06	OK	Pass
	16			24.65	OK	Pass