

Sanyo Test Report

	<u>Carryo Tost Ropore</u>
Name of Sample	Lithium Ion Battery 2UPF518175-1-T0824
Consignor	SANYO Energy(Suzhou) CO.,LTD
Manufacturer	SANYO Energy(Suzhou) CO.,LTD
Test Method	United Nations "Recomenndations on the TRANSPORT OF DANGEROUS GOODS"
Criterion	United Nations "Recomenndations on the TRANSPORT OF DANGEROUS GOODS"
Appearance	Black rectangular parallelepiped
Test Date	2011/11/04 - 2011/11/17
Sample Number	24
Test Items	Altitude simulation, Thermal test, Vibration test, Shock test, External short circuit, Overcharged
Conclusion	The sample has passed the items of UN38.3.
Remark	Certification by Similar Model: 2UPF518175-1-T0824 Ratio of (2UPF518175-1-T0824)/(2UPF518175-1-T0824) [+]=100%, [-]=100%, [Electrolyte]=100%
Consignor Address	No.86 Sunwu Road, Xukou, Wuzhong District, Suzhou City, Jiangsu Province 215164, China

Sanyo Electric Co., LTD.
Energy Devices Company
Lithium-Ion Battery Division
Battery System Development Management Department
Techinical Administration Department

Takashi Mori	6 m. Komita	m. Tokarchi
Approval	Check	Writing



B: Checklist for Judging New Type Battery or not

Confirmation of presence of change in "The element which is given influence" (Change \Rightarrow O, No change \Rightarrow -)

When there is no change in all items, it is NOT considered to be a New Type Battery.

Model which UN regulation test h	as completed	2UPF518175-1-T0824	
Target model which is not a	new type	2UPF518175-1-T0824	

Test Item (Function)	The element which is given influence	Presence of change
T1 : Altitude Simulation (Decompression load)	 Crimped part, Gasket (Cell) Gas Release Vent, Cell Case (Cell) Pack (Plastic) Case Holding Member(Insulator, Insulation Tape, Both Sides Tape) Coating materials 	_
T2:Thermal Shock (Repetition of high temp. and low temp.)	 Crimped part, Gasket (Cell) Gas Release Vent, Cell Case (Cell) Finished state of Wound Electrodes (Cell) Pack (Plastic) Case Holding Member(Insulator, Insulation Tape, Both Sides Tape) Coating materials 	_
T3:Vibration (Vibration load)	 Finished state of Wound Electrodes (Cell) Electric wiring member Electronic Parts on a circuit board Cell Holding Member (Adhesive, Both Sides Tape, Lib of Plastic Case) 	_
T4:Shock(Shock load)	 Wiring Member Electronic Parts on a circuit board Cell Holding Member(Adhesive, Both Sides Tape, Lib of Plastic Case) Finished state of Wound Electrodes (Cell) 	_
T5:External Short Circuit(Short current)	 Over-voltage Protection Current Control Device Safety Device of cell (Cell) Lead Tab 	-
T6(Cell):Impact(Crash load)	Separator (Cell) Insulation State in a cell (Cell)	_
T7(Pack): Overcharge(Charge load)	Overcharge Protection Thermal Device Safety Device of cell (Cell)	_
Judgment result	New Type or not	New Not new

Sanyo Electric Co., LTD. Energy Devices Company Lithium-Ion Battery Division

Battery System Development Management Department

Techinical Administration Department

akashi Mori

6 m. Komita

m. Takauchi

approval

Check

Writing

Certificate of UN test for Lithium ion battery

Customer Model : L11S2P01

Sanyo Model : 2UPF518175-1-T0824

Sanyo Product Code : F12272108

SANVO Electric Co.,Ltd.
Energy Devices Company
Lithium-Ion Battery Division
Battery System Development Management Department

A Lash Mori Manager
Technical Administration Department

We declare that this battery passed UN test.

Manua (38. 3	Manual of Tests and Criteria (38.3 Lithium batteries)	Test	Note	Number of test batteries	st batteries
No.	Test item	results			
⊢	T 1 Altitude simulation	Pass			
Т 2	T 2 Thermal test	Pass		First cycle	After 50 cycles
Т 3	T3 Vibration	Pass		fully charged	fully charged
Т 4	T 4 Shock	Pass		4 batteries	4 batteries
T 5	T 5 External short circuit	Pass			
9 _	T 6 Impact	Pass		First cycle 5 cells for 10 cells for	First cycle 50% charged 5 cells for cylindrical cell, 10 cells for prismatic cell,
Т 7	T 7 Overcharge	Pass	For battery only	First cycle fully charged 4 batteries	First cycle fully charged 4 batteries After 50 cycles, fully charged 4 batteries
8 L	T 8 Forced discharge	I	For cell only	For cell only.	

*The test data may contain additional test result other than avobe table.

Lithium ion battery Specification

Item	Nominal value	Note
Watt-hour rating / Rated capacity	27 Wh / 3.7 Ah	
Nominal voltage	7.4 V	
Lithium equivalent content	2.22 g	
	1 - 1 - 1 - 1 - 1	

Tests and Criteria ST/SG/AC. 10/11/Rev. 5, PartIII, sub-section 38.3) Above test procedures are compliant to the following manual. (Manual of

1.Test Item: Altitude simulation (T1)

2.Test Purpose: This test simulates air transport under low-pressure conditions.

3.Test Procedure:

Test cells and batteries shall be stored at a pressure of 11.6kPa or less for at least six hours at ambient temperature(20 ± 5 °C).

P.3/8

SANYO Internal Procedure:

As above.

4.Test Requirements:

No mass loss(less than 0.1%),no leakage,no venting,no disassembly,no rupture and no fire,and the voltage retention is not less than 90%.

The requirement relating to voltage is not applicable to test batteries at fully discharged states.

5.Test Date: 2011/11/03

6.Test Data

D 44 N	т	Mas	ss(g)	Mass	Volta	ge(V)	Voltage	Other	D 1/	T 1
Battery N	NO.	Before test	After test	loss	Before test	After test	Retentio	event	Result	Judgement
At first	1	58.910	58.920	0.02	4.17	4.16	99.8	0	PASS	
cycle,in fully	2	58.900	58.930	0.05	4.17	4.16	99.8	0	PASS	
charged	3	58.900	58.890	0.02	4.17	4.16	99.8	0	PASS	
states	4	58.940	58.930	0.02	4.17	4.16	99.8	0	PASS	PASS
After 50	5	58.880	58.900	0.03	4.19	4.18	99.8	0	PASS	rass
cycles ending in	6	59.020	59.010	0.02	4.16	4.15	99.8	0	PASS	
fully	7	58.980	59.020	0.07	4.18	4.17	99.8	0	PASS	
charged states	8	59.820	59.850	0.05	4.17	4.16	99.8	0	PASS	

1.Test Item: Thermal Test (T2)

2.Test Purpose: This test assesses cell and battery seal integrity and internal electrical connections. The test is conducted using rapid and extreme temperature changes.

3.Test Procedure:

Test cells and batteries are to be stored for at least six hours at a test temperature equal to 75 ± 2 °C, followed by storage for at least six hours at a test temperature equal to -40 ± 2 °C. The maximum time internal between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ± 5 °C). For large cells and batteries th duration of exposure to the test temperature extremes should be at least 12 hours.

SANYO Internal Procedure:

As above.

4. Test Requirements:

No mass loss(less than 0.1%),no leakage,no venting,no disassembly,no rupture and no fire,and the voltage retention is not less than 90%.

The requirement relating to voltage is not applicable to test batteries at fully discharged states.

5.Test Date: 2011/11/04-2011/11/08

6.Test Data

D 44 N	т	Mas	ss(g)	Mass	Volta	ge(V)	Voltage	Other	D 1/	T 1
Battery N	NO.	Before test	After test	loss	Before tes	After test	Retentio	event	Result	Judgement
At first	1	58.920	58.930	0.02	4.16	4.12	99.0	0	PASS	
cycle,in fully	2	58.930	58.910	0.03	4.16	4.12	99.0	0	PASS	
charged	3	58.890	58.860	0.05	4.16	4.12	99.0	0	PASS	
states	4	58.930	58.960	0.05	4.16	4.12	99.0	0	PASS	PASS
After 50	5	58.900	58.870	0.05	4.18	4.14	99.0	0	PASS	PASS
cycles ending in	6	59.010	59.030	0.03	4.15	4.12	99.3	0	PASS	
fully	7	59.020	59.010	0.02	4.17	4.14	99.3	0	PASS	
charged states	8	59.850	59.880	0.05	4.16	4.12	99.0	0	PASS	

1.Test Item: Vibration (T3)

2.Test Purpose: This test simulates vibration during transport.

3.Test Procedure:

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithm between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the direction vibration must be perpendicular to the terminal face.

The logarithmic frequency sweep is as follows: from 7 Hz a peak acceleration of 1gn is maintained until 18 reached.

The amplitude is then maintained at 0.8 mm(1.6 mm total excursion) and thefrequency increased until a pea acceleration of 8gn occurs (approximately 50Hz). A peak acceleration of 8 gn is then maintained until the free is increased to 200Hz.

SANYO Internal Procedure:

As above.

4. Test Requirements:

No mass loss(less than 0.1%),no leakage,no venting,no disassembly,no rupture and no fire,and the voltage retention is not less than 90%.

The requirement relating to voltage is not applicable to test batteries at fully discharged states.

5.Test Dat 2011/11/09-2011/11/10

6.Test Data

D 44 N	т	Mas	ss(g)	Mass	Volta	ge(V)	Voltage	Other	D 1/	T 1
Battery N	NO.	Before tes	After test	loss	Before tes	After test	Retentio	event	Result	Judgement
At first	1	58.930	58.890	0.07	4.12	4.12	100.0	0	PASS	
cycle,in fully	2	58.910	58.890	0.03	4.12	4.12	100.0	0	PASS	
charged	3	58.860	58.830	0.05	4.12	4.12	100.0	0	PASS	
states	4	58.960	58.970	0.02	4.12	4.12	100.0	0	PASS	DACC
After 50	5	58.870	58.920	0.08	4.14	4.14	100.0	0	PASS	PASS
cycles ending in	6	59.030	59.070	0.07	4.12	4.12	100.0	0	PASS	
fully	7	59.010	58.970	0.07	4.14	4.14	100.0	0	PASS	
charged states	8	59.880	59.860	0.03	4.12	4.12	100.0	0	PASS	

1.Test Item: Shock (T4)

2.Test Purpose: This test simulates possible impacts during transport.

3.Test Procedure:

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all surfaces of each test battery. Each cell or battery shall be subjected to a half-sine shock of pack acceleration of 1 and pulse duration of 6 milliseconds. Each cell or battery shall be subjected to three shocks in the positive direct followed by three shocks in the negative direction of three mutually perpendicular mounting positions of the cell for a total of 18 shocks.

P.6/8

However, large cells and large batteries shall be subjected to a half-sine shock of peak acceleration of 50 g $_{\rm n}$ and duration of 11 milliseconds. Each cell or battery is subjected to three shocks in the positive direction followed by shocks in the negative direction of each of three mutually perpendicular mounting positions of the cell for a total shocks.

SANYO Internal Procedure:

As above.

4.Test Requirements:

No mass loss(less than 0.1%),no leakage,no venting,no disassembly,no rupture and no fire,and the voltage retention is not less than 90%.

The requirement relating to voltage is not applicable to test batteries at fully discharged states.

5.Test Date: 2011/11/11

6.Test Data

75.44	т.	Mass(g)		Mass	Volta	ge(V)	Voltage	Other	D 1/	Tudasmont
Battery N	No.	Before tes	After test	loss	Before tes	After test	Retentio	event	Result	Judgement
At first	1	58.890	58.880	0.02	4.12	4.12	100.0	0	PASS	
cycle,in	2	58.890	58.900	0.02	4.12	4.12	100.0	0	PASS	
fully charged	3	58.830	58.840	0.02	4.12	4.12	100.0	0	PASS	
states	4	58.970	58.960	0.02	4.12	4.12	100.0	0	PASS	PASS
After 50	5	58.920	58.960	0.07	4.14	4.14	100.0	0	PASS	PASS
cycles ending in	6	59.070	59.070	0.00	4.12	4.12	100.0	0	PASS	
fully	7	58.970	58.950	0.03	4.14	4.14	100.0	0	PASS	
charged states	8	59.860	59.870	0.02	4.12	4.12	100.0	0	PASS]

1.Test Item: External short circuit (T5)

2.Test Purpose: This test simulates an external short circuit.

3.Test Procedure:

The cell or battery to be tested shall be temperature stabilized so that its external case temperature reaches 55 ± 2 °C and then the cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.10hm at 55 ± 2 °C. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 55 ± 2 °C. The cell or battery must be observed for a further six hours for the test to be concluded.

P.7/8

SANYO Internal Procedure:

As above.

4.Test Requirements:

External temperature of test batteries does not exceed $170\,^{\circ}$ C and there is no disassembly,no rupture and no fire within six hours of this test.

5.Test Dat (2011/11/14

6.Test Data

Bat	tery No.	Maximum temperature (°C)	Other event	Result	Judgement
At first	1	55.0	0	PASS	
cycle,in	2	54.8	0	PASS	
fully charged	3	54.6	0	PASS	
states	4	55.0	0	PASS	DACC
After 50	5	54.6	0	PASS	PASS
cycles ending in	6	54.5	0	PASS	
fully	7	54.4	0	PASS	
charged states	8	54.7	0	PASS	

Notes: D-Disassembly, R-Rupture, F-Fire, 0-No disassembly, no rupture & no fire

P. 7/8

1.Test Item: Impact (T6)

2.Test Purpose: This test simulates an impact.

3.Test Procedure:

The test sample cell or component cell is to be placed on a flat surface. A 15.8mm diameter bar is to be placed

A cylindrical or prismatic cell is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8mm diameter curved surface lying across the centre of the test sample. A prismatic cell is also to be rotated 90 degrees around its longitudinal axis so that both the wide and narrow sides will be subjected to the impact. Each sample is to be subjected to only a single impact. Separate samples are to be used for each impact.

A coin or button cell is to be impacted with the flat surface of the sample parallel to the flat surface and the 15.8mm diameter curved surface lying across its centre.

SANYO Internal Procedure:

As above.

4.Test Requirements:

External temperature of test batteries does not exceed 170°C and there is no disassembly and no fire within six hours of this test.

5.Test Date: 2009/07/23

6 Test Data

Cell No	٠.	Maximum Temperature(°C)	Other event	Result	Judgement
	1	74.5	0	PASS	
	2	84.3	0	PASS	
	3	78.9	0	PASS	
At first	4	63.5	0	PASS	
cyc l e, 50%	5	76.6	0	PASS	
charged	6	22.9	0	PASS	
states	7	77.7	0	PASS	
	8	21.4	0	PASS	PASS
	9	21.2	0	PASS	
	10	94.7	0	PASS	
	11	32.7	0	PASS	
	12	32.8	0	PASS	
After 50	13	33.6	0	PASS	
cycles	14	33.6	0	PASS	
ending, in	15	26.6	0	PASS	
fu ll y	16	30.1	0	PASS	
discharge d states	17	22.4	0	PASS	
u States	18	23.3	0	PASS	
	19	46.7	0	PASS	
	20	22.6	0	PASS	

Notes: D-Disassembly, F-Fire, 0-No disassembly & no fire

1.Test Item:Overcharge (T7)

2.Test Purpose: This test evaluates the ability of a rechargeable battery to withstand an overcharge cond **3.Test Procedure:**

P.8/8

The charge current shall be twice the manufacturer's recommended maximum continuous charge currer The minimum voltage of the test shall be as follows:

- (a) when the manufacturer's recommended charge voltage is not more than 18V, the minimum vol of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) when the manufacturer's recommended charge voltage is more than 18V, the minimum voltag of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours.

SANYO Internal Procedure:

Min.Charge Voltage	8.4 V
Charge Current:	5.4 A

4.Test Requirements:

There is no disassembly and no fire within seven days of the test.

5.Test Date: 2011/11/18

6.Test Data

Battery	No.	Event	Result	Judgement
At first	1	0	PASS	
cycle in	2	0	PASS	
fully charged states	3	0	PASS	PASS
	4	0	PASS	
After 50	5	0	PASS	rass
cycles ending in fully	6	0	PASS	
	7	0	PASS	
charged	8	0	PASS	

Notes: D-Disassembly, F-Fire, 0-No disassembly & no fire